

**August 19, 2014**

**REPORT:** The following report covers testing of the product we received from Castek® Inc. under **ASTM E 303-93 (2008)**, Standard Test Method for Measuring Surface Frictional Properties Using the British Pendulum Tester.

**PRODUCT:** The samples were labeled: **#1 Sand, Bauxite 16 x 70 and Bauxite 6 x 20.**


**SAMPLE:** Three 4" x 9" samples were received on August 15, 2014 from Reynaldo Ong of Castek® Inc.

**PROCEDURE:** The samples were measured for skid resistance in two directions and then the average was calculated.

<u>TEST METHOD</u>	<u>Sample</u>	<u>Results(average)</u>
Skid Resistance: ASTM E 303-93	#1 Sand	98.5 BPN
	Bauxite 16 x 70	98.3 BPN
	Bauxite 6 x 20	94.7 BPN

Evaluated by:

  
Roye Bruce Dawson, Lab Technician  
[Castek-Transpo\(726-728\)skid.xlsx](#)



DATE: 8/19/14

NOTARY PUBLIC: 